



PIGMENT PASTE FOR WATER BASED PAINT

GOKUL EXIMP

(STAR EXPORT HOUSE)

AN ISO 9001:2015 CERTIFIED COMPANY

25-A Juhu Supreme Shopping Center, Gulmohar Cross Road No. 9, JVPD Scheme, Mumbai 400049, India

Phone: +91-22-66923698, 66997369 Mobile : +91-9820024339 (Naveen) / 9920459697 (Rohit)

Website : www.gokuleximp.com | Email: gokuleximp@gmail.com / naveen@gokuleximp.com / rohit@gokuleximp.com

**Technical Information**

Product Name	C. I. Name	Solid Content % ±3%	Density in gm / cc	Light Fastness		Weather Fastness	
				F	T	F	T
PIGMENT YELLOW 601	PY 1	45	1.1-1.2	7	6	4	3
PIGMENT YELLOW 603	PY 3	50	1.1-1.2	7	6	4	3
PIGMENT YELLOW 674	PY 74	45	1.1-1.2	7	6	4	4
PIGMENT YELLOW 674-09	PY 74	40	1.1-1.2	6	6	4	3
PIGMENT YELLOW 683	PY 83	42	1.1-1.2	8	8	5	5
PIGMENT YELLOW 651	PY 151	40	1.1-1.2	8	8	5	5
PIGMENT ORANGE 605	PO 5	48	1.1-1.2	6	5	3	2
PIGMENT ORANGE 613	PO 13	45	1.1-1.2	6	5	3	2
PIGMENT ORANGE 634	PO 34	48	1.1-1.2	6	5	3	2
PIGMENT RED 602	PR 2	50	1.1-1.2	7	4	4	3
PIGMENT RED 608	PR 8	53	1.2-1.4	5	6	4	4
PIGMENT BORDEAUX 612	PR 12	45	1.1-1.2	7	5	4	3
PIGMENT FAST VIOLET 619	PV 19	42	1.1-1.2	7	6	5	5
PIGMENT RED 612	PR 112	52	1.1-1.2	7	6	4	4
PIGMENT RED 622	PR 122	28	1.1-1.2	8	8	5	5
PIGMENT RED 670	PR 170	45	1.1-1.2	7	7	5	4
PIGMENT RED 654	PR 254	45	1.1-1.2	8	8	5	5
PIGMENT VIOLET 623	PV 23	30	1.1-1.2	8	8	5	5
PIGMENT BLUE 615	PB 15	52	1.1-1.2	8	7	5	4
PIGMENT BLUE 616	PB 15.3	52	1.1-1.2	8	7	5	4
PIGMENT GREEN 608	PG 7	58	1.1-1.2	8	7	5	4
PIGMENT GREEN 607	PG 7	58	1.1-1.2	8	7	5	4
PIGMENT BLACK 607	P BLK 7	40	1.1-1.2	8	8	5	5
PIGMENT SYN. YELLOW OXIDE	PY 42	62	1.5-1.6	8	8	5	5
PIGMENT SYN. RED OXIDE	PR 101	62	1.7-1.8	8	8	5	5
READY MIX SHADE							
PIGMENT JOLLY HOLLY	MIXTURE	45	1.1-1.2	7	7	4	4
PIGMENT ROSSILA	MIXTURE	50	1.1-1.2	7	7	4	4
PIGMENT SUNRISE	MIXTURE	42	1.1-1.2	7	7	4	4
PIGMENT CRIMPSON RED	MIXTURE	48	1.1-1.2	7	7	4	4
PIGMENT LEMON SOUFFLE	MIXTURE	45	1.1-1.2	7	7	4	4
PIGMENT SPORTY YELLOW	MIXTURE	42	1.1-1.2	8	8	5	5
PIGMENT PARROT GREEN	MIXTURE	45	1.1-1.2	7	7	4	4
PIGMENT ORANGE VISION	MIXTURE	47	1.1-1.2	7	7	4	4
PIGMENT OLIVE GREEN INT	MIXTURE	42	1.1-1.2	6	6	4	4
PIGMENT TERRACOTTA	MIXTURE	55	1.5-1.6	8	8	5	5
PIGMENT SPL. SIGNAL RED	MIXTURE	60	1.1-1.2	8	8	4	4
PIGMENT OXFORD BLUE	MIXTURE	50	1.5-1.6	8	8	5	5
PIGMENT NAVY BLUE	MIXTURE	45	1.1-1.2	8	7	5	4
PIGMENT MEHENDI	MIXTURE	48	1.1-1.2	7	7	5	5



GOKUL EXIMP

PIGMENT PASTE FOR WATER BASED PAINT


Full Tone 5 %
Clear base

Tint Tone 5 %
In iO₂ base


Full Tone 5 %
Clear base

Tint Tone 5 %
In iO₂ base


YELLOW 601




YELLOW 603




YELLOW 674




YELLOW 674 (09)




YELLOW 683




YELLOW 651



ORANGE 605




ORANGE 613




ORANGE 634



RED 602




RED 608




BORDEAUX 612




FAST VIOLET 619




FAST RED 612




RED 622



FAST RED 670



FAST RED 654



VIOLET 623





GOKUL EXIMP

PIGMENT PASTE FOR WATER BASED PAINT

Full Tone 5 %
Clear base

Tint Tone 5 %
In iO₂ base

READY MIX SHADES

BLUE 615



BLUE 616



GREEN 608



GREEN 607




BLACK 607



SYN. YELLOW OXIDE



SYN. RED OXIDE



JOLLY HOLLY



OLIVE GREEN INT



ROSSILA




TERRACOTTA



SUNRISE



SPL. SIGNAL RED



CRIMPSON RED



OXFORD BLUE



LEMON SOUFFLE



NAVY BLUE



SPORTY YELLOW



MEHANDI



PARROT GREEN



ORANGE VISION



GOKUL EXIMP preparations are highly concentrated, free flowing, binder free pigment paste containing non ionic dispersing agents. GOKUL EXIMPPIGMENT PASTE are highly suitable for Pigmenting all aqueous media. The main field of application are on Water based decorative & exterior paints, PU Foam, Paper coating, Wood stain, Rubber.

EXPLANATION NOTES

FULL TONE: 5 Parts GOKUL EXIMP & 95 Parts Clear base

TINT : 5 Part GOKUL EXIMP & 95 Parts TiO₂ based Acrylic White emulsion.

SOLID CONTENT

5gm of GOKUL EXIMP paste accurately weighed in petri dish keep it in oven at 100°C for 3 hrs. Weigh again & calculate for solid content.

$$\text{Solid content} = \frac{100 \times W_2}{W_1}$$

W₁ = Initial weight of the paste

W₂ = weight of dried paste

FASTNESS RATINGS

The fastness ratings of shades produced with GOKUL EXIMP preparations are based primarily on individual constituent pigments. Other important factors are the pigment concentration, the nature of the binder and the formulation of medium that is to be pigmented. We therefore recommend that in each case the user carry out his own trials.

FASTNESS TO WEATHERING

The indicated ratings refer to illustrations of samples placed alongside. The change in the shade was evaluated on the grey scale.

FASTNESS TO ACID AND ALKALI

Because of various compositions of modern limes and cements, the performance of GOKUL EXIMP preparations should be checked case by case.

GOKUL EXIMP Ready Mix Shades Pigment dispersions For Exterior Paints

Highly concentrated, readily pourable pigment paste containing non ionic/anionic wetting and dispersing agents.

Their main purpose is the colouration of Acrylic Emulsion paints especially for Exterior purpose.

Having excellent Light Fastness and Weather Fastness properties.

Advantages: Uniform and Consistent shades. Avoids matching of multiple products at users end.

NOTE:

The information submitted in the publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own test and experiments, neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws legislation are observed.